

### Product Description

Stabilis HT is a single pack high temperature resistance silicone coating with maximum temperature resistance upto 700 °C.

### Features

- heat resistance upto 700 °C
- good compatibility with inorganic zinc rich coating
- Good weather resistance
- Easy to apply and fast dry.

### Typical Uses

Recommended as heat resistance paint system for various plants, steel and metal structures such as piping, vessels, reactors, furnaces, flare stack, burners, boilers, engines and exhausts where service temperature upto 700 °C.

### Physical Data

Color	:	Silver, White, Red Brown
Flash Points	:	22.3 °C
Volume Solid	:	42+/- 2%
VOC(as supplied)	:	650g/L
Shelf Life @25°C / indoor	:	24 months

Typical Thickness : 20 ~ 30µ dried film.

Drying Time(at Dry Film Thickness 20µ)	Temperature	10°C	20°C	30°C
	Surface Dry	50mins	30mins	20 mins
Hard Dry	5 hrs	3.0 hrs	1.0 hrs	
Painting interval:	Minimum	20 hrs	16 hrs	10 hrs
	Max. (self)	120days	90 days	60 days
Theoretical coverage (at DFT 20- 30µ)	0.047~0.07 L/m <sup>2</sup> ; 21.3~ 14.3 m <sup>2</sup> /L			
Service temperature	-60 to 700°C (dry)			

### Application Data

Thinner : Acrylic Thinner

Application Method : airless spray, roller, brush

Mixing Procedure : Power mix for at least two minutes or until homogeneous.

Drying schedule : Single pack and drying by solvent evaporation and oxidation. Higher

film thickness, insufficient ventilation, or lower temperature will require longer drying time. Excessive humidity or condensation on the surface can interfere with the drying cause discoloration and may result in a surface haze. Any haze or contamination must be removed by water washing before recoating.

This product requires the substrate temperature to be above the dew point (+ 3~5 °C). Condensation due to substrate temperatures below dew point can cause flash rust on metal and adhesion will be affected.

Color Different : The paint use as primer or anti fouling may have slight color variance between batches. Similarly, the paint under sun light exposure may fade and chalk.

### Application Procedure

Mix properly the paint before use.

- Flush equipment with Hana thinner A before use.
- Mix the paint thoroughly until homogeneous.
- Thin with Hana Thinner A only if necessary for workability.
- When applying by conventional spray, use adequate air pressure and volume for proper atomisation.
- Apply a wet coat in even parallel passes, overlap 50% to avoid holidays and pin hole.
- Excessive thickness can prolong drying and sagging.
- Clean up all equipment with thinner immediately after use.
- Keep containers tightly close and store in proper storage area.

### Condition of Application

Use brush or roller with 1/8" nap . Apply at sufficient thickness and avoid repeating rolling to have good levelling.

Temperature : Min 5 °C ; Max 50 °C  
Humidity : Maximum 85 % R.H.  
For Airless spray :-  
Tip Size : Graco 615, 715 or equivalent

Paint Output pressure : 10.7 – 13.8 MPa (g)  
Viscosity : 1.5 ~ 2.0 Pa.s  
Thinning : 0 – 10 % by volume

### Surface Preparation

General :

Surfaces must be clean and dry, all contaminants like dirt, dust, oil must be removed by appropriate method to ensure good adhesion.

#### Abrasive blast clean

Abrasive blast clean to Sa 2.5 (ISO-8501) or SSPC-SP6. In case of hydro blasting or hydro jetting to remove existing coating, ginger rust should be removed and blow dry before application. Surface profile must be a minimum of 50 microns.

#### Shop primed steelwork

Weld seam and damaged area should be cleaned to a minimum St3 or SSPC-SP3. The shop primed steelwork should be repaired for any rust and free from any contaminant with suitable secondary surface preparation such as spot blast, sweeping or power tooling.

### Safety Precaution and Clean-up

**Safety:** Read and follow the material safety data sheet (MSDS) before use. Employ normal safety precaution. Put on necessary personal protection equipment when handle and use this product.

**Ventilation:** when working in a confined workplace, thorough air ventilation must be used during and after application until the coating is cured. The ventilation system should be effective to prevent solvent vapour concentration from reaching lower explosion limit for the product and to ensure exposure limit to the personnel to be below permissible exposure limit.

**Caution:** All electrical equipment and installations should be properly grounded. In areas where explosion hazard exists, workmen should be used non-ferrous tools, conductive shoes and non-sparking tools.

**Clean-up:** Use Hana Paint epoxy thinner (Hana Thinner E) or hydrocarbon solvent for cleaning. Observe safety precaution when use the solvents. In case of spillage, absorb and dispose the material and used container according to local required regulation or through licensed waste collector.

#### Disclaimer

Data, specifications, directions and recommendations given in this data sheet represent test results or experience obtained under controlled or specially defined circumstances. Their accuracy, completeness or appropriateness under the actual conditions of any intended use is not guaranteed and must be determined by user. The products are delivered and any technical assistance is given subject to our GENERAL CONDITIONS OF SALE, DELIVERY AND SERVICE and, unless otherwise expressly agreed in writing, manufacturer and seller assume no liability in excess of that stated therein for results obtained, injury, direct or consequential damage incurred from the use as recommended above or otherwise.

#### Limited Warranty

Whilst we endeavour to ensure that all advice we give about this product is correct and manufacture according to standard quality control system, however we have no control over either the quality or condition of the substrate or many other factors affecting the use and application of the product. Therefore, unless we specifically agree in writing to do so, we do not accept any liability whatsoever or howsoever arising for the performance of the product or for any loss or damage arising out of the use of this product.